

常州迈特复合材料有限公司

Chang Zhou Matex Composites Co.,Ltd.

Technical Data Sheet

www.matex-frp.com info@matexcomposites.com Tel:+86 13584510068 No.8,Changwu North Road,Changzhou 213161,Jiangsu,China

RESIN FOR ARTIFICIAL STONE/BASIN (354)

Introduction

354 resin is an Ortho-phyhalic unsaturated polyester resin. The resin has moderate viscosity and reactivity, good colorability, high strength, and good toughness.

Used to mix with sand, stone and gravel, to produce: artifical marble, wash basins, kitchen countertops, bathtubs, spas, facade panel, sinks, artificial marble waistline...

Product Features

- *Good colorability
- *Moderate viscosity and reactivity
- *High strength and good toughness
- *Low shrinkage, Excellent curability

Technical Data

| Item | Unit | Value | Test Standard |
|--------------------------|---------|---------------------------------|---------------|
| Appearance | / | light yellow transparent liquid | / |
| Acid Value | mgKOH/g | 14-20 | GB2895 |
| Viscosity(25°C) | mPa.S | 350-550 | GB7193 |
| Gel Time | munites | 5-11 | GB7193 |
| Non-Volatile | % | 54-60 | GB7193 |
| Thermal Stability (80°C) | h | ≥24 | GB7193 |

Note: Gel Time is 25°C in air bath;

0.5ml cobalt isocaprylate solution and 0.5ml MEKP solution were added into 50g resin

Indexes of Resin Casting Substance

| Item | Unit | Value | Test Standard |
|---------------------|---------------|-------|---------------|
| Barcol hardness | barcol | 40 | GB3854 |
| Tensile strength | MPa | 55 | GB2567 |
| Tensile modulus | mPa.S | 3300 | GB2567 |
| Elongation at break | % | 3 | GB2567 |
| Flexural strength | MPa | 110 | GB2567 |
| Flexural modulus | MPa | 3300 | GB2567 |
| Impact strength | KJ/m2 | 8 | GB2567 |
| H.D.T | °C | 75 | GB1634.2 |
| Experiment Temper | ature: 23±2°C | | |

Relative humidity: 50±5%

Package

| Weight/drum (kg) | Drums/pallet | Quantity per 20'container | Quantity per 40'container |
|---------------------|--------------|---------------------------|---------------------------|
| 220 | 4 | 80drums = 17,600kg | 108 drums = 23,760 kg |

Storage

Shelf Time: 6 months (under 25°C environment)

Storage: 354 resin been suggested to be stocked in ventilated place, avoids direct sunlight, heat and fire.

Note: The data were tested according to GB standard. Influenced by many factors in the process of fabrication, necessary researches by user are not exclusive.

Legally, no warranties for some performances of product are applicable to one specific use and the rights to amend the materials are reserved.