



常州迈特复合材料有限公司

Chang Zhou Matex Composites Co.,Ltd.

www.matex-frp.com info@matexcomposites.com Tel:+86 13584510068

No.8,Changwu North Road,Changzhou 213161,Jiangsu,China

Technical Data Sheet

RESIN GENERAL PURPOSE (196P)

Introduction

196P is an ortho-phthalic preaccelerated type general use unsaturated polyester resin with medium viscosity, high reaction activity.

Proper for filament winding, hand lay up, open mold process, to produce: fiberglass parts, cooling towers, frp tanks, lighting poles, pipes, vessels...

Product Features

*General purpose resin, superior comprehensive performance

*High strength, good heat resistance

Technical Data

Item	Unit	Value	Test Standard
Appearance	/	Transparent Sticky Liquid	/
Acid Value	mgKOH/g	16-22	GB2895
Viscosity(25°C)	mPa.S	350-650	GB7193
Gel Time	munites	7-12	GB7193
Non-Volatile	%	62-68	GB7193
Thermal Stability (80°C)	hour	≥24	GB7193

Note: Gel Time is 25°C in air bath;

0.5ml cobalt isocaprylate solution and 0.5ml MEKP solution were added into 50g resin

Indexes of Resin Casting Substance

Item	Unit	Value	Test Standard
Barcol hardness	barcol	40	GB3854
Tensile strength	MPa	60	GB2567
Elongation at break	Mpa	3	GB2567
Flexural strength	MPa	90	GB2567
Impact strength	KJ/M2	8	GB2567
H.D.T	°C	75	GB1634.2
Experiment Temperature: 23±2°C Relative humidity: 50±5%			

Package

Weight/drum (kg)	Drums/pallet	Quantity per 20'container	Quantity per 40'container
220	4	80drums = 17,600kg	108drums = 23,760kg

Storage

Shelf Time: 6 months (under 25°C environment)

Storage: Resin been suggested to be stocked in ventilated place, avoids direct sunlight, heat and fire.

Note:The data were tested according to GB standard. Influenced by many factors in the process of fabrication, necessary researches by user are not exclusive.

Legally, no warranties for some performances of product are applicable to one specific use and the rights to amend the materials are reserved.